Reviewed on: 18 June 2012

1.	Identification of substance and manufacturer's name				
	Product details/Trade name:				
	Wangenheimstr. 37/39, D-14193 Berlin         Telephone: +49 (0) 30 / 82 00 99 0         Fax:       ++49 (0) 30 / 82 28 145         Information department/Emergency information:         Quality assurance department         e-mail: sicherheit@hoffmann-dental.com				
	e-mail: sicherneit@notimann-	Jental.com			
2.	Composition/Data on ingredients				
	Chemical characterization: Description: Mixture of water and below-mentioned substances with innocuous additions.				
	Gefährliche Inhaltsstoffe CAS 9003-01-4	Polyacrylic acid	Warning, H215	40%	
	CAS 9003-01-4	Folyaciyiic aciu	Warning; H315, H319, H335	40 %	
			Xi; R 36/37/38		
2					
3.	Hazards identification				
	Hazard designation:         Xi       Irritant         Special danger warning for human and environment:         The product has to be labelled due to the calculation procedure of the "EU-Directive of the General Classifica Preparations" in the latest valid version.         H315:       Causes skin irritation.         H319:       Causes serious eye irritation         H335:       May cause respiratory irritation         R36/37/38:       Irritating to eyes, respiratory system and skin         Classification system:       The classification is in compliance with the current EU-lists, but is also completed with details given by technoliterature and company.				
4.	First aid measures				
	General warnings: - After skin contact:	Remove contaminated clothing immediately. Remove by washing with soap under the running water. Generally the product is not irritating to skin.			
	- After eye contact:	Immediately flush opened eye ur specialist.	nder running water for several	minutes, consult an eye	
	- After swallowing:	(A plenty of substance) induce vo	omiting and consult a physicia	an.	
	- After inhaling:	Not applicable.			
5.	Fire fighting measures				
	Suitable extinguishing agents: Special protective equipment: Special information:				

## Material Safety Data Sheet according to 1907/2006/EC, Article 31 Hoffmann Dental Manufaktur GmbH

6.		
	Accidental release measures	
	Person-related safety precautions: Environmental precautions:	No special measures are required. Prevent spillage of large product amounts from entering waters and sewage system. Dilute with plenty of water.
	Methods of cleaning up:	Absorb with liquid binding material (chemical binders; use cellulose for small amounts). Remove the remainders with water and detergents.
7.	Handling and storage	
	Handling: - Information for safe handling:	The product is only for dental use. Keep containers tightly closed.
	- Information for sale handling: - Information about protection	Keep containers tightiy closed.
	against explosion and fire:	No special measures are requires.
	Storage:	
	- Information about storage:	Store dry and tightly closed in original container; frost-free and not above 25 $^\circ\mathrm{C}.$
	- Information about storage in	
	one common storage facility: - Requirements for storage rooms:	Nor required. No special requirements.
	Ingradiants with limiting values the	t require menitoring at the workplace
		t require monitoring at the workplace
	None	
	None       TLV     Not applic   Technical protective measures: Not required.	able
	None         TLV       Not applic         Technical protective measures: Not requipment:	able
	None         TLV       Not applic         Technical protective measures: Not requipersonal protective equipment:         Respiratory protection: Not required.	able
	None         TLV       Not applie         Technical protective measures: Not requiper         Personal protective equipment:         Respiratory protection: Not required.         Skin protection: Wear suitable protective product/the substance/the preparation. D	able uired. e gloves; the glove material has to be impermeable and resistant to the Due to absent tests no recommendations about the glove material can be given fo
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical	able uired. e gloves; the glove material has to be impermeable and resistant to the Due to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D the product/the preparation/the chemical breakthrough time, kinds of permeation	able uired. e gloves; the glove material has to be impermeable and resistant to the Due to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the and the degradation.
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical breakthrough time, kinds of permeation and the characteristics and varies from manufaction.	able uired. e gloves; the glove material has to be impermeable and resistant to the Due to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the and the degradation. e suitable gloves does not only depend on material but also on further qualit turer to manufacturer. As the product is a preparation of several substances, th
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical breakthrough time, kinds of permeation           Material of gloves: The selection of the characteristics and varies from manufac resistance of the glove material can not	able uired. but the glove material has to be impermeable and resistant to the bue to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the and the degradation. turer to manufacturer. As the product is a preparation of several substances, th be calculated in advance and has to be checked prior to the application. Suitabl
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical breakthrough time, kinds of permeation and the characteristics and varies from manuface resistance of the glove material can not glove material is e. g. butyl rubber, fluct maximum of 15 minutes gloves made of	able uired. e gloves; the glove material has to be impermeable and resistant to the bue to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the and the degradation. e suitable gloves does not only depend on material but also on further qualit turer to manufacturer. As the product is a preparation of several substances, the be calculated in advance and has to be checked prior to the application. Suitable procarbon rubber (Viton), natural rubber (Latex). For the permanent contact of a PVC or PE are suitable.
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical breakthrough time, kinds of permeation and the characteristics and varies from manufac resistance of the glove material can not glove material is e. g. butyl rubber, fluc maximum of 15 minutes gloves made of Penetration time of glove material: The substance of the glove material: The substance of the glove material is not glove material is the substance of the glove material is the substance of the glove material is not glove material is the substance of the glove material is not glove material is the substance of the glove material is not glove material is the substance of the glove material is not glove material is the substance of glo	able uired. e gloves; the glove material has to be impermeable and resistant to the bue to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the and the degradation. e suitable gloves does not only depend on material but also on further qualit turer to manufacturer. As the product is a preparation of several substances, the be calculated in advance and has to be checked prior to the application. Suitable procarbon rubber (Viton), natural rubber (Latex). For the permanent contact of a PVC or PE are suitable.
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical breakthrough time, kinds of permeation and the characteristics and varies from manuface resistance of the glove material can not glove material is e.g. butyl rubber, fluct maximum of 15 minutes gloves made of Penetration time of glove material: The gloves and has to be observed.           Eye protection: Protective goggles with set of the set	able uired. e gloves; the glove material has to be impermeable and resistant to the Due to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the and the degradation. e suitable gloves does not only depend on material but also on further quality turer to manufacturer. As the product is a preparation of several substances, the be calculated in advance and has to be checked prior to the application. Suitable procarbon rubber (Viton), natural rubber (Latex). For the permanent contact of a PVC or PE are suitable. exact breakthrough time is to be obtained from the manufacturer of the protective side protection are recommended.
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical breakthrough time, kinds of permeation and the characteristics and varies from manufac resistance of the glove material can not glove material is e. g. butyl rubber, fluc maximum of 15 minutes gloves made of Penetration time of glove material: The gloves and has to be observed.           Eye protection: Lightweight protective	able uired. e gloves; the glove material has to be impermeable and resistant to the Due to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the and the degradation. e suitable gloves does not only depend on material but also on further quality turer to manufacturer. As the product is a preparation of several substances, the be calculated in advance and has to be checked prior to the application. Suitable procarbon rubber (Viton), natural rubber (Latex). For the permanent contact of a PVC or PE are suitable. exact breakthrough time is to be obtained from the manufacturer of the protective side protection are recommended. clothing.
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical breakthrough time, kinds of permeation and the characteristics and varies from manuface resistance of the glove material can not glove material is e.g. butyl rubber, fluct maximum of 15 minutes gloves made of Penetration time of glove material: The gloves and has to be observed.           Eye protection: Lightweight protective General protective and hygienic measure	able uired. e gloves; the glove material has to be impermeable and resistant to the Due to absent tests no recommendations about the glove material can be given for I mixture. The selection of the glove material should be in consideration of the and the degradation. e suitable gloves does not only depend on material but also on further quality turer to manufacturer. As the product is a preparation of several substances, the be calculated in advance and has to be checked prior to the application. Suitable procarbon rubber (Viton), natural rubber (Latex). For the permanent contact of a PVC or PE are suitable. exact breakthrough time is to be obtained from the manufacturer of the protective side protection are recommended. clothing. es:
	None           TLV         Not applie           Technical protective measures: Not required.           Personal protection: Not required.           Skin protection: Wear suitable protective product/the substance/the preparation. D           the product/the preparation/the chemical breakthrough time, kinds of permeation and the characteristics and varies from manufac resistance of the glove material can not glove material is e. g. butyl rubber, fluc maximum of 15 minutes gloves made of Penetration time of glove material: The gloves and has to be observed.           Eye protection: Lightweight protective	able uired. e gloves; the glove material has to be impermeable and resistant to the Due to absent tests no recommendations about the glove material can be given fo I mixture. The selection of the glove material should be in consideration of the and the degradation. e suitable gloves does not only depend on material but also on further qualit turer to manufacturer. As the product is a preparation of several substances, the be calculated in advance and has to be checked prior to the application. Suitable procarbon rubber (Viton), natural rubber (Latex). For the permanent contact of a PVC or PE are suitable. exact breakthrough time is to be obtained from the manufacturer of the protective side protection are recommended. clothing. es:

9.	Physical and chemical properties			
	General information:			
	Form:	Liquid		
	Colour:	Colourless		
	Odour:	Odourless		
	Change in state	not datarmined		
	Boiling point/boiling range: Melting point/melting range:	not determined not determined		
	Flashpoint:	not applicable		
	pH-value:	1,5 – 2,5		
	Autoflammability:	Product does not self ignite		
	Danger of explosion:	Product is not explosive		
	Density at 20 °C:	1,1800 g/cm <sup>3</sup>		
	Solubility in water:	fully miscible		
	-			
	Solvent content:			
	Organic solvents:	0,0 %		
	Water:	60 %		
	VOC EU:	0,0 %		
10.	Stability and reactivity			
	Conditions to be avoided:	No decomposition when used according to the regulations.		
	Hazardous reactions:	No hazardous reactions are known when used according to regulations.		
	Hazardous decomposition products:	No hazardous decomposition products are known.		
	··			
11.	Toxicological information			
	Acute toxicity: Owing to the operational experience the product does not cause any noxious effects when used handled according to regulations. Primary skin irritation effect:			
	- Skin:	No irritation		
	- Eye:	No irritation		
	The product must not be labelled according to the calculation method of the ""EU-Directive of the General Classification of Preparations" in the latest version.			
12.	Ecological information			
	-			
	Referring to main substance:			
	Biological decomposition:	Is not determined.		
	Ecotoxicological information:	Quantitative data about ecological effects are not available for this		
		product.		
	Biological effects:	Not determined.		
	General information:	Water hazard class 1 (self-assessment): slight hazardous to waters.		
13.	Disposal details			
15.				
	Product:       Small amounts can be disposed of together with domestic waste.         Large amounts must be disposed of according to official regulations.			
	European Waste Catalogue			
	18 01 04 Waste, whose coll	ection and disposal is not subject to special requirements in		
	order to prevent infection			

Hoffmann Dental Manufaktur GmbH

